



## Productspecification/Information

## EDEL SOCCER FUTURE DS 60 SB-S

A	Name of product Sports application	EDEL SOCCER FUTURE DS 60 SB-S Football, Soccer
B	Producer Production process	EDEL GRASS B.V. - Genemuiden - The Netherlands tufted, cut pile
C	Pile material  Yarn Dtex Cross-section of tapes  Colour Line colour UV-stability Light fastness Colour fastness	Thiolon® PE monofilament yarn (XQ™ technology), U-shape, double spine reinforced, environment friendly, UV-stabilised 12000/6 Dtex width : 1.20 mm, ±5% thickness : 230 µm (max), ±5% bicolour (field green and lime green) white/yellow/reflex blue DIN 53387 meets 6000 hours W.O.M. test >7 on blue scale 1-8 >4 on gray scale 1-5
D	Primary backing  Coating  Water permeability	Thiobac® polypropylene double-layer, UV-stabilised, total weight ± 222 gr/m <sup>2</sup> Carboxylated (SBR) latex, appr. 988 gr/m <sup>2</sup> with 4mm perforation holes > 180 mm/h
E	Product details Pile height Total construction height Pile weight Total weight Gauge Stitch per m <sup>1</sup> linear Stitch per m <sup>2</sup> Filaments per m <sup>2</sup>	appr. 60 mm ±10% appr. 62 mm ±10% appr. 1680 gr/m <sup>2</sup> ±10% appr. 2890 gr/m <sup>2</sup> ±10% 5/8" 170 ±10 10710 ±10% 128520 ±10%
F	Infill Stabilizing infill  Amount Performance infill Amount	silica-sand, gradation 0.5 - 1.0 mm, min. 80% round of shape appr. 15 kg/m <sup>2</sup> (10 mm) SBR, gradation 0.8 - 2.5 mm appr. 15 kg/m <sup>2</sup> (30 mm)
G	Installation method Roll width Roll length Joints/seams  Line marking	loose laid on bound or unbound sub-base 4 m <sup>1</sup> (± 2 cm) according to installation schedule the seams in the turf are joined with a reinforcing tape type 220 glued to the back of the turf tufted-in or to be laid in by installation
H	Approvals	FIFA*/FIFA ** (Lab report: 29100063)

The above data are subject to modifications based on technical improvements or company-internal developments. All data are higher than the DIN-standards. All figures are average values and can vary slightly.